

### Evaluation Carbone Simplifiée des modules Soluxtec – série PowerSlate Multi Serie

Composant	240 Wc		245 Wc		250 Wc		255 Wc		260 Wc	
	Quantité par kWc	Gi kgCO2/kWc	Quantité par kWc	Gi kgCO2/kWc	Quantité par kWc	Gi kgCO2/kWc	Quantité par kWc	Gi kgCO2/kWc	Quantité par kWc	Gi kgCO2/kWc
PolySi	2.84	55.0	2.78	53.9	2.72	52.8	2.67	51.8	2.62	50.8
Lingot-Wafer	250	173.7	245	170.1	240	166.7	235	163.4	231	160.3
Cellule	250	29.6	245	29.0	240	28.4	235	27.8	231	27.3
Module	6.70	59.1	6.56	57.9	6.43	56.7	6.30	55.6	6.18	54.5
Verre	66.97	47.8	65.60	46.9	64.29	45.9	63.03	45.0	61.82	44.2
EVA	5.85	22.1	5.73	21.7	5.62	21.2	5.51	20.8	5.40	20.4
PET	2.54	8.6	2.49	8.5	2.44	8.3	2.40	8.1	2.35	8.0
PVF	0.00	0.0	0.00	0.0	0.00	0.0	0.00	0.0	0.00	0.0
<b>TOTAL</b>		<b>395.9</b>		<b>387.8</b>		<b>380.0</b>		<b>372.6</b>		<b>365.4</b>

SOLSTYCE SAS

8, rue Carnot  
93100 Montreuil

Tel : +33 1 83 62 13 29

Fax : +33 1 83 62 13 47

www.solstice.fr

